



## CUTTING CONDITIONS

## Milling | Endmills | Cutting conditions

# WX-G-ETSS



### Side milling (Contour line finish)

	C≤0,2% - GG E24 · XC48 · GG25 750 N/mm <sup>2</sup>			~30 HRC 350NCD16 · 40CMD8			SUS 316 ~ 304 800 N/mm <sup>2</sup>			30~38 HRC Z38CDV5 · Z40CDV5			45~55 HRC Z38CDV5			55~60 HRC Z160CDV12													
	Vc	100 (m/min)			80 (m/min)			80 (m/min)			60 (m/min)			60 (m/min)			30 (m/min)												
Ø	S (min <sup>-1</sup> )	F (mm/min)	AZ (mm)	S (min <sup>-1</sup> )	F (mm/min)	AZ (mm)	S (min <sup>-1</sup> )	F (mm/min)	AZ (mm)	S (min <sup>-1</sup> )	F (mm/min)	AZ (mm)	S (min <sup>-1</sup> )	F (mm/min)	AZ (mm)	S (min <sup>-1</sup> )	F (mm/min)	AZ (mm)											
3	10.610	589	0,027	8.488	458	0,018	6.366	267	0,014	6.366	344	0,018	6.366	210	0,011	3.183	105	0,011											
4	7.958	907	0,038	6.366	477	0,025	4.775	272	0,019	4.775	358	0,025	4.775	229	0,016	2.387	107	0,015											
5	6.366	955	0,05	5.093	519	0,034	3.820	298	0,026	3.820	390	0,034	3.820	241	0,021	1.910	115	0,02											
6	5.305	987	0,062	4.244	547	0,043	3.183	306	0,032	3.183	411	0,043	3.183	248	0,026	1.592	119	0,025											
8	3.979	883	0,074	3.183	535	0,056	2.387	272	0,038	2.387	401	0,056	2.387	222	0,031	1.194	107	0,03											
10	3.183	793	0,083	2.546	519	0,068	1.910	241	0,042	1.910	390	0,068	1.910	195	0,034	955	95	0,033											
12	2.653	796	0,100	2.122	497	0,078	1.592	239	0,050	1.592	372	0,078	1.592	196	0,041	796	95	0,04											
16	1.989	657	0,100	1.592	525	0,110	1.194	286	0,080	1.194	394	0,110	1.194	190	0,053	597	90	0,05											
Max cutting depth				<table><tr><td>D</td><td>ap</td><td>ae</td></tr><tr><td>&lt; 6</td><td>1,5D</td><td>0,02D</td></tr><tr><td>≥ 6</td><td>1,5D</td><td>0,05D</td></tr></table>			D	ap	ae	< 6	1,5D	0,02D	≥ 6	1,5D	0,05D	<table><tr><td>ap</td><td>ae</td></tr><tr><td>1,5D</td><td>0,02D</td></tr></table> ap max = 0,5mm			ap	ae	1,5D	0,02D	<table><tr><td>ap</td><td>ae</td></tr><tr><td>1D</td><td>0,02D</td></tr></table> ap max = 0,5mm			ap	ae	1D	0,02D
	D	ap	ae																										
< 6	1,5D	0,02D																											
≥ 6	1,5D	0,05D																											
ap	ae																												
1,5D	0,02D																												
ap	ae																												
1D	0,02D																												

Attention : sparks and/or flames can cause coolant fire. Be sure adequate fire prevention is available.

1. Speeds and feeds are designed to be used in conjunction with small passes on a high speed & precision machine.
2. Do not use inflammable coolant. Using worn tools may generate sparks.
3. Use compressed air or a high quality coolant with a low co-efficient of smoke emission.

## Slotting

	C≤0,2% - GG E24 • XC48 • GG25 750 N/mm²			~30 HRC 350NCD16 • 40CMD8			SUS 316 ~ 304 800 N/mm²			30~38 HRC Z38CDV5 • Z40CDV5			45~55 HRC Z38CDV5			55~60 HRC Z160CDV12		
	Vc 80 (m/min)			60 (m/min)			50 (m/min)			55 (m/min)			45 (m/min)			20 (m/min)		
Ø	S (min⁻¹)	F (mm/min)	AZ (mm)	S (min⁻¹)	F (mm/min)	AZ (mm)	S (min⁻¹)	F (mm/min)	AZ (mm)	S (min⁻¹)	F (mm/min)	AZ (mm)	S (min⁻¹)	F (mm/min)	AZ (mm)	S (min⁻¹)	F (mm/min)	AZ (mm)
3	8.488	688	0,027	6.897	372	0,018	5.305	223	0,014	5.836	245	0,014	4.775	158	0,011	2.122	70	0,011
4	6.366	726	0,038	5.173	388	0,025	3.979	227	0,019	4.377	249	0,019	3.581	172	0,016	1.592	72	0,015
5	5.093	764	0,050	4.138	422	0,034	3.183	248	0,026	3.501	273	0,026	2.865	180	0,021	1.273	76	0,020
6	4.244	789	0,062	3.448	445	0,043	2.653	255	0,032	2.918	280	0,032	2.387	186	0,026	1.061	80	0,025
8	3.183	707	0,074	2.586	434	0,056	1.989	233	0,039	2.188	256	0,039	1.790	167	0,031	796	72	0,030
10	2.546	672	0,088	2.069	422	0,068	1.592	224	0,047	1.751	247	0,047	1.432	146	0,034	637	63	0,033
12	2.122	637	0,100	1.724	403	0,078	1.326	215	0,054	1.459	236	0,054	1.194	147	0,041	531	64	0,040
16	1.592	573	0,120	1.293	388	0,100	995	239	0,080	1.094	263	0,080	895	142	0,053	398	60	0,050
Max cutting depth	 <div style="display: flex; justify-content: space-around; align-items: center;"> <div> <math>ap = 0,3D</math>  <math>ap \text{ max} = 3mm</math> </div> <div> <math>ap \text{ max} = 0,2D</math> </div> </div>																	

Attention : sparks and/or flames can cause coolant fire. Be sure adequate fire prevention is available.

1. Speeds and feeds are designed to be used in conjunction with small passes on a high speed & precision machine set-up.
2. Do not use inflammable coolant. Using worn tools may generate sparks.
3. Use compressed air or a high quality coolant with a low co-efficient of smoke emission.